



Protective & Marine Coatings

METALASTIC® DTM ACRYLIC MODIFIED ENAMEL

B55Z-600 SERIES

Revised 7/10

PRODUCT INFORMATION

2.24

PRODUCT DESCRIPTION

METALASTIC DTM is a VOC compliant, high-build acrylic modified enamel with rust-inhibitive properties for application directly to bare steel. Provides an economical alternative to many maintenance and new construction projects.

- VOC compliant
- Good gloss and color retention
- Corrosion resistance and finish coat protection in one coat
- Outstanding long term performance
- Excellent application properties

PRODUCT CHARACTERISTICS

Finish:	Semi-Gloss
Color:	Wide range of colors available
Volume Solids:	59% ± 2%, may vary by color
Weight Solids:	76% ± 2%, may vary by color
VOC (EPA Method 24):	Unreduced: <330 g/L; 2.75 lb/gal Reduced 3½%: <340 g/L; 2.8 lb/gal

Recommended Spreading Rate per coat:

	Minimum	Maximum
Wet mils (microns)	5.0 125	8.0 200
Dry mils (microns)	3.0 75	5.0 125
~Coverage sq ft/gal (m²/L)	190 4.7	315 7.2
Theoretical coverage sq ft/gal (m²/L) @ 1 mil / 25 microns dft	944 23.1	

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Drying Schedule @ 7.0 mils wet (175 microns):

	@ 40°F/4.5°C	@ 77°F/25°C 50% RH	@ 120°F/49°C
To touch:	3 hours	1.5 hours	45 minutes
To handle:	10 hours	6 hours	1 hours
To recoat:	36 hours	18 hours	6 hours
To cure:	14 days	7 days	7 days

Drying time is temperature, humidity, and film thickness dependent.

Shelf Life:	36 months, unopened Store indoors at 40°F (4.5°C) to 100°F (38°C).
Flash Point:	120°F (49°C), PMCC
Reducer/Clean Up:	
Below 80°F (27°C):	VM&P Naphtha, R1K3
Above 80°F (27°C):	Hi-Flash Naphtha, R2K5

RECOMMENDED USES

For use over prepared steel in industrial environments.

- Interior / exterior
- New construction
- Machinery
- Structural steel
- Steel doors
- Steel decking
- Suitable for use in USDA inspected facilities
- Conforms to AWWA D102 OCS #1
- Primer / finish
- Repaints
- Storage tank exteriors
- Bar joists
- Piping
- Conveyors

PERFORMANCE CHARACTERISTICS

Substrate*: Steel

Surface Preparation*: SSPC-SP6/NACE 3

System Tested*:

2 cts. Metalastic DTM @ 3.0 mils (75 microns) dft
*unless otherwise noted below

Test Name	Test Method	Results
Abrasion Resistance	ASTM D4060, CS17 wheel, 1000 cycles, 1 kg load	50 mg loss
Adhesion	ASTM D4541; ASTM D3359	420 psi (ASTM D4541); 5B (ASTM D3359)
Corrosion Weathering	ASTM D5894, 2 cycles, 672 hours	Rating 10 per ASTM D610 for rusting
Direct Impact Resistance	ASTM D2794	50 in. lbs.
Dry Heat Resistance	ASTM D2485	200°F (93°C) (discolors)
Flexibility	ASTM D522, 180° bend, 1/4" mandrel	Passes
Moisture Condensation Resistance	ASTM D4585, 100°F (93°C), 1000 hours	Rating 10 per ASTM D610 for rusting
Pencil Hardness	ASTM D3363	3B
Salt Fog Resistance	ASTM B117, 1000 hours	Rating 10 per ASTM D610 for rusting

Provides performance comparable to products formulated to federal specifications: MIL-E-15090, TT-E-485F

continued on back



**Protective
&
Marine
Coatings**

**METALASTIC® DTM
ACRYLIC MODIFIED ENAMEL**

B55Z-600 SERIES

PRODUCT INFORMATION

2.24

RECOMMENDED SYSTEMS

	Dry Film Thickness / ct.	
	Mils	(Microns)
Steel, Light Service:		
1 ct. Metalastic DTM	3.0-5.0	(75-125)
Steel, Moderate Service:		
2 cts. Metalastic DTM	3.0-5.0	(75-125)

The systems listed above are representative of the product's use, other systems may be appropriate.

SURFACE PREPARATION

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Refer to product Application Bulletin for detailed surface preparation information.

Minimum recommended surface preparation:
Iron & Steel: SSPC-SP2

Condition of Surface	Surface Preparation Standards		SSPC	NACE
	ISO 8501-1 BS7079:A1	Swedish Std. SIS055900		
White Metal	Sa 3	Sa 3	SP 5	1
Near White Metal	Sa 2.5	Sa 2.5	SP 10	2
Commercial Blast	Sa 2	Sa 2	SP 6	3
Brush-Off Blast	Sa 1	Sa 1	SP 7	4
Hand Tool Cleaning	C St 2	C St 2	SP 2	-
Pitted & Rusty	D St 2	D St 2	SP 2	-
Rusty	C St 3	C St 3	SP 3	-
Power Tool Cleaning	D St 3	D St 3	SP 3	-

TINTING

Tint with BAC or Maxitoner colorants at 100% strength. Five minutes minimum mixing on a mechanical shaker is required for complete mixing of color.

APPLICATION CONDITIONS

Temperature: 40°F (4.5°C) minimum, 120°F (49°C) maximum (air, surface, and material)
Relative humidity: At least 5°F (2.8°C) above dew point
85% maximum

Refer to product Application Bulletin for detailed application information.

ORDERING INFORMATION

Packaging: 1 gallon (3.78L) and 5 gallon (18.9L) containers
Weight: 11.5 ± 0.2 lb/gl, 1.38 Kg/L
may vary with color

SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.



Protective & Marine Coatings

METALASTIC® DTM ACRYLIC MODIFIED ENAMEL

B55Z-600 SERIES

Revised 7/10

APPLICATION BULLETIN

2.24

SURFACE PREPARATIONS

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Iron & Steel

Minimum surface preparation is Hand Tool Clean per SSPC-SP2. Remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. For better performance, use Commercial Blast Cleaning per SSPC-SP6/NACE 3, blast clean all surfaces using a sharp, angular abrasive for optimum surface profile (2 mils / 50 microns). Coat any bare steel within 8 hours or before flash rusting occurs.

Previously Painted Surfaces

If in sound condition, clean the surface of all foreign material. Smooth, hard or glossy coatings and surfaces should be dulled by abrading the surface. Apply a test area, allowing paint to dry one week before testing adhesion. If adhesion is poor, or if this product attacks the previous finish, removal of the previous coating may be necessary. If paint is peeling or badly weathered, clean surface to sound substrate and treat as a new surface as above.

APPLICATION CONDITIONS

Temperature: 40°F (4.5°C) minimum, 120°F (49°C) maximum
(air, surface, and material)
At least 5°F (2.8°C) above dew point

Relative humidity: 85% maximum

APPLICATION EQUIPMENT

The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.

Reducer/Clean Up

Below 80°F (27°C) VM&P Naphtha, R1K3
Above 80°F (27°C)..... Hi-Flash Naphtha, R2K5

Airless Spray

Pressure..... 2400 psi
Hose..... 3/8" ID
Tip015"
Filter 60 mesh
Reduction..... Not recommended

Conventional Spray

Gun Binks 95
Fluid Nozzle 63B
Air Nozzle..... 63PB
Atomization Pressure..... 50 psi
Fluid Pressure..... 20-25 psi
Reduction..... As needed, up to 3½% by volume

Brush

Brush..... Natural Bristle
Reduction..... As needed, up to 3½% by volume

Roller

Cover 3/8" woven with solvent resistant core
Reduction..... As needed, up to 3½% by volume

If specific application equipment is not listed above, equivalent equipment may be substituted.

Surface Preparation Standards

Condition of Surface	ISO 8501-1 BS7079:A1	Swedish Std. SIS055900	SSPC	NACE
White Metal	Sa 3	Sa 3	SP 5	1
Near White Metal	Sa 2.5	Sa 2.5	SP 10	2
Commercial Blast	Sa 2	Sa 2	SP 6	3
Brush-Off Blast	Sa 1	Sa 1	SP 7	4
Hand Tool Cleaning	C St 2	C St 2	SP 2	-
Pitted & Rusted	D St 2	D St 2	SP 2	-
Rusted	C St 3	C St 3	SP 3	-
Power Tool Cleaning	D St 3	D St 3	SP 3	-

continued on back



Protective & Marine Coatings

METALASTIC® DTM ACRYLIC MODIFIED ENAMEL

B55Z-600 SERIES

APPLICATION BULLETIN

2.24

APPLICATION PROCEDURES

Surface preparation must be completed as indicated.

Mixing Instructions: Mix paint thoroughly to a uniform consistency with low speed power agitation prior to use.

Apply paint at the recommended film thickness and spreading rate as indicated below:

Recommended Spreading Rate per coat:

	Minimum	Maximum
Wet mils (microns)	5.0 125	8.0 200
Dry mils (microns)	3.0 75	5.0 125
~Coverage sq ft/gal (m²/L)	190 4.7	315 7.2
Theoretical coverage sq ft/gal (m²/L) @ 1 mil / 25 microns dft	944 23.1	

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Drying Schedule @ 7.0 mils wet (175 microns):

	@ 40°F/4.5°C	@ 77°F/25°C 50% RH	@ 120°F/49°C
To touch:	3 hours	1.5 hours	45 minutes
To handle:	10 hours	6 hours	1 hours
To recoat:	36 hours	18 hours	6 hours
To cure:	14 days	7 days	7 days

Drying time is temperature, humidity, and film thickness dependent.

Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.

CLEAN UP INSTRUCTIONS

Clean spills and spatters immediately with VM&P Naphtha, R1K3. Clean tools immediately after use with VM&P Naphtha, R1K3. Follow manufacturer's safety recommendations when using any solvent.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

PERFORMANCE TIPS

Stripe coat all crevices, welds, and sharp angles to prevent early failure in these areas.

When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. If necessary, cross spray at a right angle.

Spreading rates are calculated on volume solids and do not include an application loss factor due to surface profile, roughness or porosity of the surface, skill and technique of the applicator, method of application, various surface irregularities, material lost during mixing, spillage, overthinning, climatic conditions, and excessive film build.

Excessive reduction of material can affect film build, appearance, and adhesion.

In order to avoid blockage of spray equipment, clean equipment before use or before periods of extended downtime with VM&P Naphtha, R1K3.

Refer to Product Information sheet for additional performance characteristics and properties.

SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.